

Chapter 15.04 SUBDIVISIONS

Section 15.04.700 Road subgrade preparation.

In both cut and fill areas the paving subgrade shall be scarified to a depth of eight inches and compacted to the equivalent of ninety-six (96) percent of maximum dry density, as measured by AASHTO T-99. No rocks larger than two inches in diameter, organic material, soft clay, spongy material, or other deleterious material will be permitted in this scarified subgrade layer. Rough subgrades shall be shaped and graded to within a tolerance of 0.10 foot of design grade and drainage shall be maintained at all times.

During the rolling operation moisture content of the subgrade layer shall be maintained at not less than ninety-seven (97) percent or more than one hundred five (105) percent of optimum moisture content. Rolling shall be continued until the entire roadbed is compacted to the specified density to a minimum depth of eight inches. (Ord. 5-1988 § 1 (part): Development Code 4-5-6)