

[Chapter 15.04 SUBDIVISIONS](#)

Section 15.04.800 Depositing.

Concrete shall be deposited as nearly as practical in its final position to avoid segregation due to rehandling or flowing. The concrete placing shall be carried on at such a rate that the concrete is at all times plastic and flows readily into the corners of forms and reinforcing bars. No concrete that has partially hardened or been contaminated by foreign material shall be deposited in the work, nor shall retempered concrete be used. No concrete shall be dropped more than three feet.

All concrete in structures shall be vibrator compacted during the operation of placing, and shall be thoroughly worked around reinforcement and embedded fixtures and into the corners of the forms. (Ord. 5-1988 § 1 (part): Development Code 4-6-9)